



Epoxy Compound

DENACOL EX-171


Product feature

- Mono-Functional Aliphatic type
- Water solubility

Application

- Hydrophilizing agent
- Reactive diluent

Chemical structure/name



Lauryl Alcohol (EO)₁₅ Glycidyl Ether

General Properties

| Epoxy equivalent (g/eq.) | Viscosity (mPa·s) | Total chlorine content (%) | Color value (APHA) | Water solubility (%) |
|--------------------------|-------------------|----------------------------|--------------------|----------------------|
| 971 | - (mp.40°C) | 1.7 | 10 | 100 |

Each property and data introduced in this catalog, it is a representative value, NOT a guaranteed value. Also, please note that the specifications of the products are subject to change without notice.

Please read the Safety Data Sheet(SDS) before use.

More Information

Nagase ChemteX Corporation

Functional Chemicals Department
236, Tatsunocho-nakai Tatsuno Hyogo
679-4124 JAPAN
TEL:+81-791-63-4528 FAX:+81-791-63-4564
E-mail: denacol.info@ncx.nagase.co.jp



Nagase ChemteX