



Epoxy Compound

DENACOL EX-252


Product feature

- Di-Functional Aliphatic type
- Hydrophobic
- High weather resistant

Application

- Crosslinker for paint
- UV curing resin

Chemical structure/name



Hydrogenated Bisphenol A Diglycidyl Ether

General Properties

Epoxy equivalent (g/eq.)	Viscosity (mPa·s)	Total chlorine content (%)	Color value (APHA)	Water solubility (%)
213	2,200	4.5	10	Insoluble

Each property and data introduced in this catalog, it is a representative value, NOT a guaranteed value. Also, please note that the specifications of the products are subject to change without notice.

Please read the Safety Data Sheet(SDS) before use.



Nagase ChemteX Corporation

Functional Chemicals Department 236, Tatsunocho-nakai Tatsuno Hyogo 679-4124 JAPAN

TEL:+81-791-63-4528 FAX:+81-791-63-4564 E-mail: denacol.info@ncx.nagase.co.jp

