



Epoxy Compound

DENACOL EX-821


Product feature

- Di-Functional Aliphatic type
- Water solubility
- Low viscosity
- Flexibility

Application

- Crosslinker for waterborne resin
- Hydrophilizing agent
- Flexibility-imparting agent

Chemical structure/name



Polyethylene Glycol Diglycidyl Ether

General Properties

| Epoxy equivalent (g/eq.) | Viscosity (mPa·s) | Total chlorine content (%) | Color value (APHA) | Water solubility (%) |
|--------------------------------|----------------------|----------------------------------|-----------------------|-------------------------|
| 185 | 40 | 4.5 | 30 | 100 |

Each property and data introduced in this catalog, it is a representative value, NOT a guaranteed value. Also, please note that the specifications of the products are subject to change without notice.

Please read the Safety Data Sheet(SDS) before use.



More Information

Functional Chemicals Department 236, Tatsunocho-nakai Tatsuno Hyogo 679-4124 JAPAN

TEL:+81-791-63-4528 FAX:+81-791-63-4564 E-mail: denacol.info@ncx.nagase.co.jp

