

Epoxy Compound

DENACOL EX-861


Product feature

- Di-Functional Aliphatic type
- Water solubility
- Flexibility

Application

- Crosslinker for waterborne resin
- Hydrophilizing agent
- Flexibility-imparting agent

Chemical structure/name



Polyethylene Glycol Diglycidyl Ether

General Properties

Epoxy equivalent (g/eq.)	Viscosity (mPa·s)	Total chlorine content (%)	Color value (APHA)	Water solubility (%)
551	- (mp.45°C)	1.5	20	100

Each property and data introduced in this catalog, it is a representative value, NOT a guaranteed value. Also, please note that the specifications of the products are subject to change without notice.

Please read the Safety Data Sheet(SDS) before use.

More Information

Nagase ChemteX Corporation

Functional Chemicals Department
236, Tatsunocho-nakai Tatsuno Hyogo
679-4124 JAPAN
TEL:+81-791-63-4528 FAX:+81-791-63-4564
E-mail: denacol.info@ncx.nagase.co.jp



Nagase ChemteX